

HEGSEL Pox 414

2-C- primer and laminating resin

Description: 2-component colourless, primer and laminating resin based on an epoxy resin.

- Characteristics:**
- Direct adhering primer on steel and concrete surfaces
 - Excellent chemical resistance
 - High temperature resistance up to +160°C (dry)

Applications: HEGSEL Pox 414 serves as a primer for HEGSEL Mortars products based on phenol and furan resins. An acidification is not necessary. On concrete surfaces HEGSEL Pox 414 has the additional function of a sealing.

Chemical resistance: Information on the chemical resistance is available on request.

Substrate: Components to be brick lined or laminated shall be de-signed and manufactured in accordance with EN 14879-1. Before start of coating work or brick lining work, the suitability of the surface preparation measures according EN 14879-1 must be checked and recorded.

Consumption:

Substrate	Coverage (g/m ²)
Steel	ca. 250
Concrete	ca. 300-350

Pot life (20°C):

Product	Time (min)
HEGSEL Pox 414	ca. 60

Curing (20°C):

Load Capacity	Time
Over workable	ca. 18 h
Accessible	ca. 18 h

Packaging: The products are supplied in the following standard package sizes:

Product	Size	Article No.
HEGSEL Pox 414 SOLUTION	20 kg	17761815
HEGSEL Pox 414 HARDENER	8 kg	17761845
HEGSEL Pox 414 CLE	25 kg	17762760
HEGSEL Pox 414 DEF	0.25 kg	17762763
Cleaner E-200	4 kg	17701830
Cleaner E-200	8 kg	17701833

Storage: The products must be stored in a cool and dry place, away from direct sunlight. At the specified storage temperatures, a shelf life of the products is given of at least for the following periods:
If the storage time is exceeded, the materials must be tested before use. Higher storage and transport temperatures will reduce the shelf life. The containers must be kept tightly closed. Liquid products must be stored frost-proof. In addition, the DIN 7716 must be observed.

Product	Temperature	Shelf Life
HEGSEL Pox 414 SOLUTION	≤ +25°C kg	24 Months
HEGSEL Pox 414 HARDENER	≤ +25°C kg	24 Months
HEGSEL Pox 414 CLE	-	24 Months
HEGSEL Pox 414 DEF	≤ +20°C kg	24 Months
Cleaner E-200	5 - 25°C	60 Months

1. Surface preparation

C-STEEL

All surfaces to be coated must be dry and free of contaminants. All contaminants, including non-visible detectable contaminants, must be removed in accordance with DIN SPEC 55684 or EN ISO 8502. Non-alloyed steel surfaces shall be abrasive blasted to "Near White Metal" in accordance with EN ISO 12944-4. A surface preparation degree of SA 2½ (SSPC- SP 10; NACE No. 2) as specified in EN ISO 8501-1 and a "medium (G)" roughness degree as specified in EN ISO 8503-2 must be achieved.

A minimum surface profile of $Rz \geq 70 \mu\text{m}$ is required. To prevent flash rust, the primer must be applied immediately after the blasting and cleaning of the substrate or the component must be air conditioned to a relative humidity of $\leq 40\%$.

CONCRETE

Appropriate action shall be taken to prepare the concrete surfaces; dry and free of dust and free of contaminants such as oil or grease. The concrete shall have minimum tensile strength of 1.5 N/mm^2 . The residual moisture content must not exceed 4%.

2. Environmental conditions

The specified environmental conditions must be observed during surface preparation and brick lining and be tested and recorded according to EN 14879-6.

Environmental conditions	Value
Relative Humidity	$\leq 80\%$
Surface Temperature	$\geq +10^\circ\text{C}$ up to $+30^\circ\text{C}$
Application Temperature	$+20^\circ\text{C} \pm 5^\circ\text{C}$ recommended
Dew Point Distance	min. 3K

3. Application

The execution of the coating and brick lining work is only permitted, if the requirements of "Surface Pre-treatment" and "Environmental Conditions" are met.

HEGSEL Pox 414 is applied twice (undiluted) by using brushes, wide brushes or rollers. If the overworking time is > 24 hours, the last coat must be sanded in fresh state with dry quartz sand (0.3 - 0.7 mm) - if no sanding is carried out - it must be grinded.

4. Work tools

The following tools are essential for the application:

- Stirrer (max. 300 r/min.)
- Measuring cup & Mixing vessels
- Flat / wide brush
- Lamb's wool roller
- Miscellaneous (safety glasses, rubber gloves etc.)

5. Mixing ratio

HEGSEL Pox 414 must be well stirred before adding the **HEGSEL Pox 414 HARDENER** in the recommended ratio. The stirring of the merged components should be at least 3 minutes and must result in a homogeneous mixture. Then pour the mixture into a clean pail and mix again briefly.

HEGSEL Pox 414	Parts by Weight (kg)	Parts by Volume (Liter)
HEGSEL Pox 414 SOLUTION	100	2.00
HEGSEL Pox 414 HARDENER	40	0.81

6. Cleaning

Clean all equipment with **Cleaner E-200** or **HEGSEL Pox 414 CLE** immediately after use. The cleaning is done while the material is still not hardened.

7. Safety measures

The material safety data sheets of the individual components, the safety instructions on the packing (label) as well as the legal requirements for handling hazardous materials must be observed.

Technical Data	Standard	Unit	Value
Density (Mixture)	EN ISO 2811 (ASTM D1475)	g/cm^3	1.14
Adhesion Strength Concrete	EN ISO 4624 (ASTM D7234)	N/mm^2	> 1.5
Adhesion Strength Steel	EN ISO 4624 (ASTM D4541)	N/mm^2	> 7
Hardness Shore D	-	-	> 70
Max. Operating Temperature Liquids	-	$^\circ\text{C}$	+160

Note: The indicated temperatures are dependent on the present load and may vary

HEGSEL Pox 414; Revision No: 1.00 / Last Revision Date: 20.10.2020

All information contained herein is based on the current state of our knowledge and practical experience at the time of release. Therefore, please make sure that this is the actual edition of the Technical Data Sheet. All data are only intended as a guideline for informational purposes and do not constitute a legally-binding warranty of the suitability for a certain purpose of use, due to its dependence on site conditions and possible processing, use and applications. All information contained in this technical datasheet is subject to change without notice.

HEGSEL GmbH
Huttropstr. 60
45138 Essen
Germany
Tel: +49 201 17003 270
Fax: +49 201 17003 277
E-Mail: info@heggel.de
Web: www.heggel.de